

Friction results of the yarn analysed

	Yarn to Yarn	Yarn to Metal
Shetland Wool (two plied yarn)		
Untreated Wool	75.20	65.68
Conventional dyeing	66.60	50.08
Liposome dyeing	77.60	61.52
Shetland Wool (two plied yarn)		
Untreated Wool	27.44	35.30
Conventional dyeing	22.00	34.56
Liposome dyeing	23.68	34.24
Wool Yarn 2/70 (one single strand yarn)		
Untreated Wool	35.68	38.08
Conventional dyeing	33.96	27.68
Liposome dyeing	34.84	23.60